

WHAT IS CLAIMED IS:

1. A molding composition comprising:

(A) an aggregate;

at least one of (B) a linear unsaturated polyester and

5 (C) a linear unsaturated polyester polyamide; and

(D) a radical generator,

wherein each of said Component (B) and (C) has a content  
of an alkylene (having from 2 to 4 carbon atoms) oxide adduct  
of bisphenol A (average added number of mols: 1 to 10) of 3  
10 to 50 mol% based on an amount of constituent monomers of each  
of said Components (B) and (C).

2. The molding composition according to Claim 1,  
wherein said Component (A) is a fibrous material.

3. The molding composition according to Claim 1,  
wherein each of said Component (B) and (C) has an iodine value  
of 70 to 150.

20 4. The molding composition according to Claim 1,  
wherein the contents of said Component (A), the sum of said  
Components (B) and (C), and said Component (D) are from 29 to  
99% by weight, from 0.5 to 70% by weight, and from 0.1 to 30%  
by weight, respectively, based on the total amount of the  
25 composition.

5. The molding composition according to Claim 1,  
wherein each of said Components (B) and (C) has a softening  
point of 80°C to 130°C.

5

6. The molding composition according to Claim 1,  
wherein each of said Components (B) and (C) has at least one  
addition-polymerizable unsaturated group in an amount of 35  
to 70% by weight based on an amount of constituent monomers  
10 of each of said Components (B) and (C).

7. A molded article obtained by molding the molding  
composition according to Claim 1.